RECEIVED CENTRAL FAX GENTER

AUG 0 4 2008

AMENDMENTS TO THE CLAIMS:

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

- 1. (Original) A medical implant or device at least partially fabricated from a metal alloy consisting essentially of
 - (a) 98.85 99.15 weight percent Niobium,
 - (b) 0.85 -1.15 % weight percent Zirconium.
- 2. (Original) A medical implant or device according to claim 1 wherein said metal alloy consists essentially of
 - (a) 99.02 –99.15 weight percent Niobium,
 - (b) 0.85 0.98 % weight percent Zirconium.
- 3. (Original) A medical implant or device according to claim 1 wherein said metal alloy consists essentially of
 - (a) 99.05 –99.15 weight percent Niobium,
 - (b) 0.85 0.95 % weight percent Zirconium.
- 4. (Currently Amended) A medical implant or device according to any one of claims 1 to 3, which is [[a]] a catheter or a guide wire.
- 5. (Previously Presented) A medical implant or device according to any one of the claims 1 to 3, which is an intra-cavernous implant.
- 6. (Previously Presented) A medical implant or device according to claim 5, wherein the intra-cavernous implant is an intravascular implant.

USSN 10/705,566 Page 2
Amendment under 37 CFR § 1.116 filed on August 4, 2008

- 7. (Previously Presented) A medical implant or device according to claim 6, which is a stent, a stent graft, a stent graft connector or a heart valve repair device.
- 8. (Previously Presented) A medical implant or device according to claim 7, which is a stent composed of a single homogeneous, substantially non-decomposing tubing made from a metal alloy consisting essentially of
 - (a) 98.85 99.15 weight percent Niobium,
 - (b) 0.85 -1.15 % weight percent Zirconium.
- 9. (Previously Presented) A medical implant or device according to claim 8, which is a stent composed of a single homogeneous substantially non-decomposing sheet made from a metal alloy consisting essentially of
 - (a) 98.85 99.15 weight percent Niobium,
 - (b) 0.85 -1.15 % weight percent Zirconium.
- 10. (Original) A medical implant or device according to any one of claims 1 3, wherein the surface of the metal alloy is passivated by oxidation or nitridization.
- 11. (Original) A medical implant or device according to any one of claims 1 3, wherein the surface of the metal alloy is coated with iridium oxide by vapor deposition.
- 12. (Original) A medical implant or device according to any one of claims 1 3, wherein the surface of the metal alloy is electropolished, mechanically polished, micro blasted, roughened or sintered.
- 13. (Original) A medical implant or device according to any one of claims 1 3, wherein the surface of the metal alloy is coated with a polymer, a blend of polymers, a metal, a blend of metals, a ceramic and/or biomolecules, in particular peptides, proteins, lipids, carbohydrates and/or nucleic acids.

USSN 10/705,566 Page 3 Amendment under 37 CFR § 1.116 filed on August 4, 2008

- 14. (Previously Presented) A medical implant or device according to any one of claims 1 3, wherein the surface of the metal alloy is coated with stem cells and/or a bioactive substance.
- 15. (Previously Presented) A medical implant or device according to claim 14, wherein the surface of the metal alloy is coated with a bioactive substance selected from the group consisting of drugs, antibiotics, growth factors, anti-inflammatory agents and/or anti-thrombogenic agents.
- 16. (Withdrawn) A method of implanting a medical implant into a patient's body, said method comprising implanting into the patient's body an implant at least partially fabricated from a metal alloy consisting essentially of
 - (a) 98.85 99.15 weight percent Niobium,
 - (b) 0.85 -1.15 % weight percent Zirconium.
- 17. (Withdrawn) A method according to claim 16, wherein the medical implant is a stent.
- 18. (Withdrawn) A method according to claim 17, wherein the stent is composed of a single homogeneous, substantially non-decomposing tubing made from the metal alloy.
- 19. (Withdrawn) A method according to claim 17, wherein the stent is composed of a single homogeneous substantially non-decomposing sheet made from the metal alloy.